

OPTIMIZATION OF HEAT TREATMENT OF Nd-Fe-B-BASED ALLOYS FOR PREPARATION OF HIGH COERCIVITY PERMANENT MAGNETS

Yu.S. Koshkid'ko^{1,5}, K. Skotnicová^{1,}, T. Čegan¹, M. Lesňák¹, O. Životsky¹, K. Hrabovská¹, K. Mamulová Kutláková¹, A.A. Lukin², A.G. Dormidontov², V.V. Sitnov², V.P. Menushenkov³, N.B. Kolchugina⁴, J. Cwik⁵, L. Snášelová¹

¹VSB – Technical University of Ostrava, Faculty of Metallurgy and Materials Engineering, Dep. Regional Materials Science and Technology Centre, Av. 17. listopadu 15, 70833 Ostrava-Poruba, Czech Republic, email: Katerina.Skotnicova@vsb.cz

²"JSC SPETSMAGNIT", Dmitrovskoe sh. 58, Moscow, 127238 Russia, e-mail: lukinikul@rambler.ru

³National Research Technological University "MISiS", 119049, Leninskij prospect 4, Moscow, Russia. <u>menushenkov@gmail.com</u>

⁴Baikov Institute of Metallurgy and Materials Science, Russian Academy of Sciences, Leninskii pr., 49, Moscow, 119991 Russia, e-mail: natalik@imet.ac.ru

⁵International LaboratoryofHighMagneticFields and LowTemperatures, 53-421, PolandWroclaw, Gajowicka str., 95, e-mail: cwikjac@ml.pan.wroc.pl

Abstract

Optimization of conditions of heat treatment of Nd-Fe-B-based permanent magnets, prepared using the strip casting method, was carried out with the aim to enhance their coercivity H_{CJ} and maximal energy product (BH)max, and to improve the shape of the demagnetization curve. The initial alloy with the chemical composition (for high-coercivity magnets) of Fe - 67.05; Nd - 19.50; B - 1; Dy - 6.00; Pr - 6.00; Cu - 0.15; Al - 0.30 (wt. %) in form of strips was submitted to hydrogen decrepitation and vibration milling. The obtained powder with the granulometry of 3-5 µm was mixed with 2.5 wt.% NdH₂ in order to improve the improvement sintering process of liquid-phase and to increase the coercivity as a result of formation of continuous grain boundary. Structural characteristics and phase composition were investigated using scanning electron microscopy equipped with EDX microprobe, light optical microscopy equipped with digital camera and XRPD. The microhardness of the principal Nd(R)₂Fe₁₄B phase was measured. Magnetic properties were evaluated using automatic hysteresisgraph and vibrating-sample magnetometer. The maximal values of the coercive force H_{CJ} of 1470 kA/m were achieved by the heat treatment at 500 °C. An increase of this temperature to 550 °C led to a sharp drop in magnetic properties and microhardness. Specially designed Zeiss microscope was used to visualize the magnetic domain patterns on the surface of magnetic materials using the magneto-optical Kerr microscopy. The observed star-like domain structure indicates a good magnetic texture for permanent magnets. These data are of great importance for choosing the optimum heat treatment of Nd-Fe-B-based magnets.

Keywords: permanent magnets, strip casting, magnetic domain structure, X-ray diffraction analysis.

1. INTRODUCTION

Sintered Nd-Fe-B magnets find wide applications in technology thanks to the high maximum energy product (BH)_{max}, residual inductance (B_r), and magnetization coercive force (H_{CJ}). Nd-Fe-B permanent magnets are used in many fields of industry. One of the problems of use of permanent magnets based on the Nd₂Fe₁₄B compound is the preservation of high magnetic properties at high temperatures. Addition of heavy rare earths of Dy or Tb effectively enhances coercivity and consequent thermal stability of the Nd-Fe-B magnets,



because Dy or Tb increases the magnetic anisotropy field of the Nd₂Fe₁₄B compound [1-2]. However, the search of the optimal composition for the magnetic properties and preparation of technological process for manufacture of permanent magnets is difficult. Some of these problems can be solved using the technology of strip casting. However, during the milling process partial oxidation of the phase rich in rare earth metals can occur. This may lead to a deterioration of sintering process of the liquid-phase due to the reduced amount of liquid phase. Formation of grain boundaries thus becomes difficult. This can lead to a decrease of the coercive force of permanent magnets, because a H_c value largely depends on the state of the grain boundaries [3-5]. This problem can be partly solved by selecting the optimum heat treatment. However, this is not enough. For this reason, the authors of this article proposed to add a hydride rare earth metal at the milling step. In addition, the authors have determined the optimal heat treatment for the developed highly coercive magnet.

2. EXPERIMENTAL

The initial alloy with the chemical composition (for high-coercivity magnets) of Fe – 67.05; Nd – 19.50; B - 1; Dy = 6.00; Pr = 6.00; Cu = 0.15; AI = 0.30 (wt.%) in the form of strips was prepared from "flakes" ~0.3 mm thick by strip-casting procedure. Linear velocity of the copper wheel was 1-2 m/s. The next step - hydrogen decrepitation – were carried out for 1-2 h at a "dry" hydrogen pressure of 1 atm; the subsequent cooling was realized at room temperature in a nitrogen atmosphere (it is desirable to discharge the powder on the next day). The milling in a vibration milling was carried out in isopropyl alcohol or freon. Neodymium hydride (2.5 wt%) was added at the grinding stage, in order to improve sintering of the liquid-phase. The minimum powder particle size was 3-4 µm. The pressing force was 1.5-2 t/cm² at a magnetic field of 2 T (pressing of parts in transverse field (TP)). The sintering was carried out at 1080 °C for 2 h (Sample N0). In search of the optimum conditions of heat-treatment, annealing was performed progressively at 500 °C (Sample N1), 530 °C (Sample N2), 550 °C (Sample N3) for 1 h each. After each stage, the gas (nitrogen, argon) quenching was carried out. Magnetic properties of the samples of permanent magnet were measured using a hysteresisgraph HG 200 and vibrating sample magnetometer, which was carried out at the International Laboratory of High Magnetic Fields and Low Temperatures in Wroclaw. The high-resolution field emission gun-scanning electron microscope QUANTA 450 FEG equipped with an EDX APOLLO X microprobe was applied for the investigation of microstructure and chemical composition of samples [6]. The XRPD patterns were recorded under CoK α irradiation (λ = 0.1789 nm) using the Bruker D8 Advance diffractometer (Bruker AXS) equipped with a fast position sensitive detector VANTEC 1. Measurements were carried out in the reflection mode, powder samples were pressed in a rotational holder. Specially designed Zeiss microscope was used to visualize the magnetic domain patterns on the surface of magnetic materials using the magnetooptical Kerr microscopy.

3. RESULTS AND DISCUSSION

3.1 SEM/EDX analysis

The stoichiometric composition of grains in all samples is close to that of the Nd₂Fe₁₄B phase (Phase 1 in Fig. 1). The ideal Fe/R ratio (R = Dy, Pr, Dy) should be \div 7. However, as is seen from the calculation of the Fe/R ratio in Table 1, some differences take place. This is related to the existence of errors of determination of the phase composition, which are due to the closeness of characteristic X-ray spectra of some elements. In particular, the excitation potential for the L_α – series of Dy is 6.494 keV, whereas for Fe, the excitation potential for Fe K_α is 6.403 keV. Therefore, we must take spectra with the lower intensity; this can give error in determining the quantitative phase composition of material. In this case for Dy, we used the Mα (1.293 keV) characteristic radiation for Dy. Another difficulty exists in determining the chemical composition for the area (since the electron beam diameter is ~ 2 µm).



Based on the analysis of chemical composition, the presence of REM oxide phases in ternary junctions of samples is assumed (Phase 2 and 3 in Fig. 1). According to literature data [7-9], ternary junctions can contain different oxide phases. These are NdO (the oxygen content is 50 at.%), Nd₂O₃ (the oxygen content is 60 at.%) [9-10], and NdO₂ (the oxygen content is 67 at.%) [3].

The atomic percentage of elements in ternary junctions corresponds to phases with the stoichiometric compositions close to the Nd_2O_3 or NdO phases. The presence of these phases in the samples was also confirmed by the X-ray diffraction analysis data.

Sampla	Phase	ОК	DyM	AIK	TiK	PrL	NdL	FeK	СоК	CuK	Fe/R
Sample		(at.%)						ratio			
	1	7.26	2.14	1.55	0.29	2.78	9.29	75.91	0.27	0.51	5.52
N0	2	45.68	3.04	0.59	0.31	7.14	19.89	23.09	0.11	0.17	
	3	56.69	2.25	0.20	0.13	7.30	21.57	11.65	0.00	0.21	
	1	8.12	2.12	1.32	0.27	2.17	9.55	75.41	0.52	0.51	5.64
N1	2	44.54	3.115	0.735	0.26	6.115	18.96	25.96	0	0.32	
	3	48.04	2.69	0.98	0.25	6.13	18.81	22.72	0	0.38	
	1	7.79	2.62	1.68	0.33	2.46	8.62	75.79	0.17	0.54	5.73
N2	2	48.86	2.69	0.07	0.23	7.18	21.00	19.52	0.00	0.45	
	3	63.44	2.30	0.15	0.21	4.55	13.52	14.60	0.58	0.65	
	1	8.69	2.52	1.26	0.24	2.46	8.4	75.41	0.37	0.66	5.82
N3	2	46.35	3.64	0.18	0.36	7.30	22.55	18.60	0.31	0.72	
	3	33.59	2.44	0.62	0.22	3.40	11.02	48.17	0.12	0.43	

 Table 1 Average chemical composition of phases observed in samples N0-N3.



Fig. 1 SEM image of N0 (a), N1 (b), N2 (c) and N3 (d) samples with marking of analyzed phases.





3.2 X-ray diffraction analysis

Figure 2 demonstrates comparison of the experimental X-ray diffraction pattern (colored lines) and pattern simulated for the Nd₂Fe₁₄B-type structure (space group P42/mnm) (black lines). It can be seen that main reflections simulated for the Nd₂Fe₁₄B coincide adequately with those in the experimental X-ray diffraction pattern; some reflections are likely to belong to other phases. These reflections are observed at 2O angles of 35.59; 36.07 and 49.97 deg. Subsequent analysis of experimental X-ray diffraction patterns was performed in detail using literature data and simulated X-ray diffraction patterns. It is known from literature that the presence of α -Fe phase can affect the properties of permanent magnets [5]. However, we failed to detect the α -Fe phase at the background of reflections of the Nd₂Fe₁₄B phase. The presence of the α -Fe phase in all four samples could be revealed by thermal magnetic analysis. Based on the analysis of chemical composition and literature data [7-9], we assumed the presence of REM oxide phases in ternary junctions of investigated samples. According to the literature data, ternary junctions can contain different oxide phases. These are NdO with the NaCl-type structure (space group Fm-3m) [9] (the oxygen content is 50 at.%), Nd₂O₃ with the La₂O₃-type structure (space group Pm-3m) (the oxygen content is 67 at.%) [2, 3], and NdO₂ with the CaF₂-type structure (space group Fm-3m) (the oxygen content is 67 at.%) [9].



Fig.2 X-ray diffraction pattern for the sample N 0-3 (λ =0.1789 nm).

The patterns in Fig. 2, simulated for the structures of the NdO and Nd_2O_3 oxides, agree adequately with the experimental patterns. A slight difference can be explained by the fact that the simulation was performed for the NdO and Nd_2O_3 compounds, whereas, according to chemical analysis data, these compounds can contain Dy and Pr, i.e., and they can differ from the composition preset by the simulation program.

Moreover, we found the shift of reflections for the samples Nos. 0-3 relatively to each other (Fig. 2). This is possibly related to the changes in the lattice parameters of the principal Nd₂Fe₁₄B phase. The calculated lattice parameters of the phase are given in Table 2.

For the sample N3 the peak of the oxide phase significantly increased. This might have been caused by the increased number of the oxide phase. Modification of the lattice parameter is associated with diffusion of atoms from the phase rich in rare earth metals in the grain.

240

BH, kJ/m³



	a (nm)	c (nm)	c/a
N0	0.8794	1.21923	1.386
N1	0.87933	1.21934	1.386
N2	0.87929	1.21975	1.387
N3	0.87941	1.22007	1.387

Table 2 Calculated lattice parameters for the phase with the Nd₂Fe1₄B-type structure for all samples.

3.3 Magnetic properties

4πM, T

Preliminary studies of magnetic properties with use of magnetic hysteresisgraph showed that the sample N1 has the best magnetic properties. However the value of the coercive force exceeds the limits of measuring of the magnetic field for hysteresisgraph (1465 kA/m). Therefore, a more detailed study of the magnetic properties of the sample N1 was conducted using a vibrating sample magnetometer.

Figure 3a shows the demagnetization curve for the sample of the permanent magnet N1. This curve was constructed from the experimental data obtained by using a vibrating sample magnetometer. When constructing the demagnetization curve the demagnetizing field of the sample was taken into account. Figure 3b demonstrates the determination of the maximum energy product (BH)max. As it can be seen from the graph, this value reaches (BH)max = 231 kJ/m3. This value is typical for high-coercivity magnets. The basic magnetic properties of the sample of the permanent magnet N1 are shown in Table 3.

Further increase in the temperature of heat treatment reduces the value of the coercive force. For the sample N3 it can be seen that as a result of heat treatment at 550 °C a sharp drop in coercive force occurred. Perhaps this is due to the process of formation of grain boundaries during heat treatment or to an increase of the oxide phase. It also confirms the decrease in the microhardness of the sample N3 (Table 4).

Br	H _{CJ}	Н _{СВ}	H _k	(BH) _{max}	
Т	kA/m	kA/m	kA/m	kJ/m³	
1.1	1470	808	909	231	

H, kA/m



Table 3 Magnetic properties of the permanent magnet N1 (heat treatment at 500 °C).

Fig. 3 Magnetic properties of the sample of the permanent magnet N1 at room temperature: a) demagnetization curves, b) the dependence of B on BH.



Samle	HV _{av} [-]	Standard deviation [-]		
N ₀	611.68	101.48		
N ₁	524.29	97.21		
N ₂	535.34	98.47		
N ₃	397.69	41.65		

 Table 4 Microhardness of the N0, N1, N2 and N3 samples.

3.4 Structure of magnetic domain

The domain structure of the samples of permanent magnets was observed at low magnetic fields (practically in remnant state). Investigations were carried out at the Institute of Physics (VSB-TUO). Study of the structure of magnetic domain was carried out on the sample surface, which was perpendicular to the axis of the texture. Red squares in Fig. 4 highlight the areas, where the magnetic domain structure of sample N1 was observed. The domain structure is possibly present on the entire surface of the sample. However, the domain structure in the remaining region could not be detected due to surface roughness. The pattern shows the so-called star-like domains and it is characteristic for uniaxial materials observed on the basal plane of single crystals Nd₂Fe₁₄B [10-11]. The observed type of domain structure indicates good magnetic texture for a permanent magnet. In few cases we found that magnetic domains were extended over the grain boundaries into neighboring grains, which could be attributed to the exchange interactions between the grains. Similar situation is observed for example in the article [12].



Fig. 4 The specimen surface of a permanent magnet N1observed in a polarized light. Red squares highlight the areas with a magnetic domain structure. Magnetic field -0.07 mT.

CONCLUSIONS

The process has optimized sintering of the liquid-phase by adding neodymium hydride. Optimal modes of heat treatment were determined. It was possible to increase the coercivity force of permanent magnets by forming continuous grain boundaries. As a result of the experiment the samples were obtained of the high-coercivity magnet having the following magnetic properties: $H_{CJ} = 1470 \text{ kA/m}$, $B_r = 1.1 \text{ T}$ and $(BH)_{max} = 231 \text{ kJ/m}^3$.



ACKNOWLEDGEMENTS

This paper was created in the project No. LO1203 "Regional Materials Science and Technology Centre – Feasibility Program" funded by Ministry of Education, Youth and Sports.

REFERENCES

- [1] LIU, W.Q., SUN, H., YI, X.F., LIU, X.C., ZHANG, D.T., YUE, M., ZHANG, J.X. Coercivity enhancement in Nd–Fe–B sintered permanent magnet by Dy nanoparticles doping. *Journal of Alloys and Compounds*, 2010, vol. 501, 67-69.
- [2] KOLCHUGINA, N., LUKIN, A., BURKHANOV, G. S., SKOTNICOVÁ, K., DRULIS, H., PETROV, V. Role of terbium hydride additions in theformationofmicrostructure and magnetic properties of sintered Nd-Pr-Dy-Fe-B magnets. In *Metal 2012: 21th International Conference on Metallurgy and Materials*. May 23rd-25th 2012 Brno, Czech Republic. 1st ed. Ostrava: Tanger s.r.o., 2012, pp. 1387-1392.
- [3] VIAL, F., JOLY, F., NEVALAINEN, E., SAGAWA, M., HIRAGA, K., PARK, K.T. Improvement of coercivity of sintered NdFeB permanent magnets by heat treatment. *Journal of Magnetism and Magnetic Materials*, 2002, vol. 242-245, pp. 1329-1334.
- [4] KOSHKID'KO, Y.S., SKOTNICOVÁ, K., KURSA, M., ČEGAN, T., BURKHANOV, G.S., KOLCHUGINA, N.B., LUKIN, A.A., DORMIDONTOV, A.G., SITNOV, V.V. The effect of heat treatment under various conditions on microstructure of sintered (Nd,Pr,Dy)-Fe-B magnets. In *METAL 2014: 23rd International Conference on Metallurgy and Materials*, Conference Proceedings May 21nd-23^{td} 2014 Brno, Czech Republic. 1st ed. Ostrava: Tanger s.r.o., 2014, pp. 1369-1374.
- [5] BAI, G., GAO, R.W., SUN, Y., HAN, G.B., WANG, B. Study of high-coercivity sintered NdFeB magnets. *Journal of Magnetism and Magnetic Materials*, 2007, vol. 308, pp. 20-23.
- [6] POHLUDKA, M., MALCHARCZIKOVA, J., MICHENKA, V., KURSA, M., ČEGAN, T., SZURMAN, I. Structure and mechanical properties of nickel alloys. In *Metal 2013: 22th International Conference on Metallurgy and Materials.* May 15th-17th 2012 Brno, Czech Republic. 1st ed. Ostrava: Tanger s.r.o., 2013, pp. 1567-1572.
- [7] KIM, T-H., LEE, S-R., NAMKUMG, S., et al. A study on the Nd-rich phase evolution in the Nd–Fe–B sintered magnet and its mechanism during post-sintering annealing. *Journal of Alloys and Compounds*, 2012, vol. 537, pp. 261-268.
- [8] WANG, S.C., LI, Y. In situ TEM study of Nd-rich phase in NdFeB magnet. Journal of Magnetism and Magnetic Materials, 2005, vol. 285, pp. 177-182.
- [9] WATANABE, N., UMEMOTO, H., ITAKURA, M., NISHIDA, M., MACHIDA, K. Grain Boundary Structure of High Coercivity Nd-Fe-B Sintered Magnets with Tb-Metal Vapor Sorption. *IOP Conf. Series: Materials Science and Engineering*, 2009, vol.1, pp. 012033.
- [10] PASTUSHENKOV, Yu.G., FORKL A., KRONMÜLLER H. Temperature dependence of the domain structure in Fe14Nd2B single crystals during the spin-reorientation transition. Journal of Magnetism and Magnetic Materials, 1997, vol. 174, No. 3, pp. 278–288.
- [11] SUBKOVA, A.V., ZEZIULINA, P.A., KOSHKID'KO, Yu.S., SIMONOV, V.V., SKOKOV, K.P., PASTUSHENKOV Yu.G. Temperature behaviour of magnetic domain structure in RE-3d intermetallics with spin-reorientation transitions. *Solid State Phenomena*, 2011, vol. 168-169, pp. 122-125.
- [12] LÖEWE, K., BROMBACHER, C., KATTERB M., GUTFLEISCH, O. Temperature-dependent Dy diffusion processes in Nd-Fe–B permanent magnets. *Acta Materialia*, 2015, vol. 83, pp. 248-255.